

Extrusion  
Injection Moulding

## E-CR glass

3B E-CR glass is boron-free and presents significantly improved corrosion resistance across a wide range of aggressive environments.

3B glass is E-CR according to ASTM D578 and ISO 2078. This translates into important benefits for end-users over traditional E-glass: longer service life, larger safety coefficients for the same design, and material savings.

Traditional E-glass includes boron and often contains added fluorides. By using new manufacturing technology to eliminate these components from the glass composition, 3B E-CR glass has become a benchmark for integrated pollution prevention and the highest energy efficiency – all in an optimized process.

3B measures its efforts and works continually to minimize its impact on the environment and to set new standards within the global fibreglass industry. This is our commitment.

## DS 3307-10N

Chopped Strand for Polyesters & Styrenics



### Product Description

DS 3307-10N is a 10 µm-filament chopped glass fibre designed to reinforce PBT, PET and their relative blends.

It is also suitable to reinforce styrenics.

DS 3307-10N glass fibre's length is 4 mm.

Its fine filament diameter provides maximised mechanical performances.

DS 3307-10N is also designed to fit well in flame-retardant as well as HR formulations.

DS 3307-10N exhibits very low fuzz and excellent dispersion, thanks to its pelletized form.

DS 3307-10N is APE-free, PFA-free and BPA-free, thus complying with the most stringent regulations.

| FEATURES                         | BENEFITS  |
|----------------------------------|---|
| Advanced sizing technology       | Suitable for PBT, PET and Styrenics<br>Suitable for a wide range of grades (FR, IM...)<br>No APE, no PFA, no BPA  |
| Versatile chopped strand product | Designed for a wide range of applications in Automotive and E&E   |
| High bulk density                | Superior feeding behaviour<br>Low fuzz generation<br>Excellent dispersion<br>Suitable for pneumatic conveying and megacomponders<br>Better productivity for reduced cleaning downtime |

# DS 3307-10N

Chopped Strand for Polyesters & Styrenics



## PRODUCT CHARACTERISTICS

| Product name | Fibre diameter<br>µm | Fibre length<br>mm | Solid content<br>% | Moisture content<br>% |
|--------------|----------------------|--------------------|--------------------|-----------------------|
| DS 3307-10N  | 10                   | 4                  | 0.91               | Max 0.05              |

## FOOD CONTACT & DRINKABLE WATER APPLICATIONS

The product has been designed in order to help reinforced plastics comply with the food contact and drinkable water norms listed below. For more detailed information and relative conditions of applicability, please refer to the official statements.

| FOOD | WATER | NORM      |
|------|-------|-----------|
| X    |       | FDA (USA) |

## PACKAGING

Standard packaging for DS 3307-10N chopped strand is 1,150 kg polypropylene bag with bottom discharge (1 bag/pallet).

## STORAGE

It is recommended to store chopped strand products indoor. The product should remain in its original packaging, on closed conditions. In order to prevent static electricity and humidity problems, the chopped strand material must be conditioned in the working place just prior to use.

In case a packaging unit is only partly used, it should be immediately re-sealed.

For safety reasons, it is recommended to store the pallets in a single stack manner.



## Customer Service

Rue de Maestricht 67

B- 4651 Battice

P. +32 87 692211

3B-thefibreglasscompany@3b-fibreglass.com

**Disclaimer of Liability** The data and information set forth in this publication is provided exclusively with the view to facilitating the selection of a product and/or service. The information contained in this publication is based on actual laboratory data and/or field test experience. We believe this information to be accurate, but do not guarantee in any manner its suitability to the user's process or assume any liability arising out of its use or performance. The user, by ordering the products and/or services described herein, agrees to be entirely responsible for thoroughly testing any application to determine its suitability before committing to production. It is key for the user to determine the properties of its own products and/or compounds when using a product and/or service herein described. We do not give any representation or warranty, express or implied, as to the accuracy or completeness of the data and information contained in this document, and shall have no liability to the user or any other person resulting from the use of or reliance on any such information. Further, we do not give any representation or warranty, express or implied, as to our products and/or services, including in respect of their merchantability and fitness for a particular purpose, and shall have no liability to the user or any other person resulting from the use of or reliance on any such products and/or services. Only those representations and warranties set forth in a supply agreement, when, as and if it is executed, and subject to such limitations and restrictions as may be set forth in such agreement, shall have any legal effect. Statements included in this document are not, and may not be construed as, representations or warranties or as inducements to infringe any patent or violate any law, safety code or insurance regulation. 3B reserves the right to modify the content of present document without notice and without incurring in any obligations.