

Stitched Mat
Stitched Mat Fabrics

E-CR glass

3B E-CR glass is boron-free and presents significantly improved corrosion resistance across a wide range of aggressive environments.

3B glass is E-CR according to ASTM D578 and ISO 2078. This translates into important benefits for end-users over traditional E-glass: longer service life, larger safety coefficients for the same design, and material savings.

Traditional E-glass includes boron and often contains added fluorides. By using new manufacturing technology to eliminate these components from the glass composition, 3B E-CR glass has become a benchmark for integrated pollution prevention and the highest energy efficiency – all in an optimized process.

3B measures its efforts and works continually to minimize its impact on the environment and to set new standards within the global fibreglass industry. This is our commitment.

CR3037

Choppable Roving for UP



Product Description

3B Choppable Roving CR3037 consists of multiple continuous strands of smaller tex made from 3B E-CR glass wound onto a bobbin shape without mechanical twist and is free from static electricity generation.

Choppable Roving CR3037 is silane sized and specifically designed to

produce single or multi-layer fabrics for automobile, boat building, chemical tanks. CR3037 is also recommended for continuous filament wind application to manufacture pipes and tanks.

3B Choppable Roving CR3037 conforms to BS 14020 and IS 11320.

FEATURES	BENEFITS
Boron free E-CR glass	High corrosion resistance
Easy unwinding and excellent chopping	No interruption while processing, hence higher productivity
Excellent dispersion and even distribution	Good fabrics coverage
Good splitting efficiency & low fuzz formation	Minimal damage of fibre while processing, hence higher mechanical properties
Good wet-out and impregnation	High laminate properties

CR3037

Choppable Roving for UP

PRODUCT CHARACTERISTICS

Product name	Filament diameter µm	Linear density - tex gm/km	Solid content % by weight	Moisure content %
CR3037	13	2400	0.7	Max 0,2
CR3037	13	4800	0.7	Max 0,2

PACKAGING

Bobbins are individually tack wrapped for protection, improved handling and to allow optimum transfer from bobbin to bobbin. Nominal weight of bobbin is around 17kg. A pallet of size 92cm x 110cm contains 48 bobbins and 110cm x 110cm contains 64 bobbins and stretch wrapped with plastic film for protection.

Two pallet configurations are available:

- Bulk-pack: standard packaging, consists of individual bobbins
- Creel-pack: bobbins are connected together for continuous unwinding and no bobbin handling by operators

STORAGE

Storage vertically in a cool and dry warehouse into the original packaging is formally recommended. More precisely ideal storage conditions are a temperature between 15°C & 35°C and a relative humidity comprised between 35% & 75%. If these conditions are maintained, the glass fibre product should not undergo significant changes when stored for extended periods of time. It is also strongly recommended to condition it in the workshop for at least 24hours before use to prevent condensation. For an optimal processing we recommend to use the product in ambient conditions (20°C-30°C and a relative humidity of 60%-65%).

Binani



B R A J B I N A N I G R O U P

Customer Service India

Survey No 220,Village Colvale
Taluka, Bardez, Goa-403 513, India
P. +91 832-2299 884/886
F. +91 832-2299 887
E. goa@3b-fibreglass.com

Customer Service Office

Ildefonse Vandammestraat 5-7
B-1560 Hoeilaart, Belgium
P. +32 2 402 2000
F. +32 2 402 2002
E. 3B-thefibreglasscompany@3b-fibreglass.com

Disclaimer of Liability The data and information set forth in this publication is provided exclusively with the view to facilitating the selection of a product and/or service. The information contained in this publication is based on actual laboratory data and/or field test experience. We believe this information to be accurate, but do not guarantee in any manner its suitability to the user's process or assume any liability arising out of its use or performance. The user, by ordering the products and/or services described herein, agrees to be entirely responsible for thoroughly testing any application to determine its suitability before committing to production. It is key for the user to determine the properties of its own products and/or compounds when using a product and/or service herein described. We do not give any representation or warranty, express or implied, as to the accuracy or completeness of the data and information contained in this document, and shall have no liability to the user or any other person resulting from the use of or reliance on any such information. Further, we do not give any representation or warranty, express or implied, as to our products and/or services, including in respect of their merchantability and fitness for a particular purpose, and shall have no liability to the user or any other person resulting from the use of or reliance on any such products and/or services. Only those representations and warranties set forth in a supply agreement, when, as and if it is executed, and subject to such limitations and restrictions as may be set forth in such agreement, shall have any legal effect. Statements included in this document are not, and may not be construed as, representations or warranties or as inducements to infringe any patent or violate any law, safety code or insurance regulation. 3B reserves the right to modify the content of present document without notice and without incurring in any obligations.