

Injection moulding, RTM, S-RIM, Infusion

Advantex[®] glass

Advantex[®] glass is a boron-free glass and presents significantly improved corrosion resistance across a wide range of aggressive environments. Advantex[®] glass is an E-CR glass in accordance with ASTM D578 and ISO 2078. This translates into important benefits for end-users over traditional E glass: longer service life, larger safety coefficients for the same design, and material savings. Traditional E-glass includes boron

and often contains added fluorides. By using new manufacturing technology to eliminate these compo-nents from the glass composition, Advantex® glass has become a benchmark for integrated pollution prevention and the highest energy efficiency – all in an optimized process.3B measures its efforts

and works continually to minimize its impact on the environment and to set new standards within the global fibreglass industry.

This is our commitment.

www.3B-fibreglass.com

CM 4020

CFM for Closed Mold Process



Product Description

3B Continuous Filament Mat is a nonwoven mat made out of ECR glass filaments, consisting of continuous fibres randomly oriented in multiple layers. The glass fibre is bonded with a silane coupling agent and the layers held together with a suitable binder. The CFM products contain an insoluble binder compatible with both unfilled or filled unsaturated polyester, vinyl, ester, epoxy and polyurethane resin systems. The CM 4020 mat is ideally suited for injection moulding RTM and S-RIM processes. The CM 4020 mat has a high rigidity which helps to work with large CFM cuts without loosing fibres. The excellent mechanical properties provided by CM 4020 combined with the good electrical properties of the resins make the moulded parts attractive for applications like the electrical apparatus (high voltage), transportation and automotive industries, infrastructures equipments.

FEATURES	BENEFITS
· Insoluble binder	 Easy unrolling, cutting and handling of the mat without loosing the mat integrity even with large parts. Good resistance to washing effect under injection pressure.
· Low bundle tex	 Improved mechanical properties of the laminate

CM 4020 CFM for Closed Mold Process

PRODUCT CHARACTERISTICS							
Product name	Weight ⁽¹⁾ g/m²	width ⁽²⁾ cm	Bundle density tex	Solid content %	Resin compatibility	Process	
CM 4020	300 - 450 - 600	130-260	20	3,75	PU, VE, EP, UP	MDM, RTM, S-RIM, Infusion	

(1) other weights available upon request

(2) other widths available upon request

PACKAGING

The 3B Continuous Filament Mat is wound on a hard carton tube with an inside hole of 102 mm and an external diameter of 110 mm. A PE stretch film is wrapped around the roll to protect the material during handling and to help the slicing. All CFM rolls have 2 sides trimmed.

The outside diameter of the roll is a standard of 55 cm.

· For mat widths up to 210 mm:6 vertical rolls per pallet

· For mat widths above 210 mm: 6 horizontal rolls per pallet Each roll is identified by a roll label

Each pallet is identified by minimum one pallet label including the date and the pallet weight. The load is fixed to the pallet with a stretch film.

For more details on packaging, please contact the technical person.

STORAGE

Storage in a cool and dry warehouse into the original packaging is formally recommended. More precisely ideal storage conditions are a temperature between 15°C and 35°C and a relative humidity comprised between 35% and 75%. If these conditions are maintained, the glass fibre product should not undergo significant changes when stored for extended periods of time. It is also strongly recommended to condition it in the workshop for at least 24 hours before use to prevent condensation. For an optimal processing we recommend to use the product in ambient conditions (20°C-23°C and a relative humidity of 60%-65%).



Customer Service office: I. Vandammestraat 5-7 Bat B B-1560 Hoeilaart, Belgium phone +32 2 402 2000 fax +32 2 402 2002 General info: 3B.info@3b-fibreglass.com

Disclaimer of Liability This data is offered solely as a guide in the selection of a reinforcement. The information contained in this publication is based on actual laboratory data and/or field test experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any liability arising out of its use or performance. The user, by accepting the products and/

or services described herein, agrees to be responsible for thoroughly testing any application to determine its suitability before committing to production. It is important for compounds when using this or any other reinforcement.

BECAUSE OF NUMEROUS FACTORS AFFECTING RESULTS. WE MAKE NO WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLU-DING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTI-CULAR PURPOSE, STATEMENTS IN THIS DATA SHEET SHALL NOT BE CONSTRUED AS REPRESENTATIONS OR WA RANTIES OR AS the user to determine the properties of its own commercial INDUCEMENTS TO INFRINGE ANY PATENT OR VIOLATE ANY LAW. SAFETY CODE OR INSURANCE REGULATION.