

Gypsum process  
Wet laid process

## E-CR glass

3B E-CR glass is boron-free and presents significantly improved corrosion resistance across a wide range of aggressive environments.

3B glass is E-CR according to ASTM D578 and ISO 2078. For end-users, this translates into important benefits over traditional E-glass: longer service life, larger safety coefficients for the same design, and material savings.

Traditional E-glass includes boron and often contains added fluorides. By using new manufacturing technology to eliminate these components from the glass composition, 3B E-CR glass has become a benchmark for integrated pollution prevention and the highest energy efficiency – all in an optimized process.

3B measures its efforts and works continually to minimize its impact on the environment and to set new standards within the global glassfibre industry. This is our commitment.

[www.3B-fibreglass.com](http://www.3B-fibreglass.com)

## WS 6050-16W

Wet Chopped Strand for Gypsum applications



### Product Description

WS 6050-16W is designed to reinforce gypsum wallboards with glass fibre.

Its sizing has been specifically developed to enhance gypsum adhesion to glass fibre, to provide outstanding fibre dispersion and distribution in gypsum slurry and superior flowability of the fibre.

As a result, this product exhibits very good feeding properties to deliver a dosing flow consistency, and to drastically improve fire resistance and mechanical properties of the gypsum boards.

#### FEATURES

Innovative sizing technology

Versatile chopped strand product

High fibre flowability

#### BENEFITS

Compatibility with gypsum slurry  
Excellent fibre dispersion  
High fibre flowability

Designed for a wide range of applications, especially in gypsum boards, including fire retardant boards

Superior feeding behaviour to deliver a dosing flow consistency

# WS 6050-16W

Wet Chopped Strand for Gypsum applications

## PRODUCT CHARACTERISTICS

Product name	Filament diameter	Fiber length	Solid content	Moisture content
	µm	mm	%	%
WS 6050-16W	16	6	0,17	max 8
WS 6050-16W	16	13	0,17	max 8

## PACKAGING

Standard packaging for WS 6050-16W Wet Chopped Strand is a 1000 or 1150 kg polypropylene bag, with a conical bottom discharge.

Plastic sheets are placed on the top of the bag and the load is fixed to the pallet with a stretch film (1 bag/pallet).

Pallet size: 1150 x 1150 mm.

Packaging in smaller quantities is available on request.

## STORAGE

It is recommended to store wet chopped strand products indoor at room temperature and at a relative humidity of 50% ± 15%.

The product should remain in its original packaging, sealed bags away from all sources of heat to avoid moisture loss, and away from low temperature to prevent it from freezing.

It is recommended that material must be conditioned in the working place just prior to use. In case a packaging unit is only partly used, it should be immediately re-sealed.

# Binani



**B R A J B I N A N I G R O U P**

### Customer Service Office

Ildefonse Vandammestraat 5-7

B-1560 Hoeilaart, Belgium

P. +32 2 402 2000

F. +32 2 402 2002

E. 3B-thefibreglasscompany@3b-fibreglass.com

**Disclaimer of Liability** The data and information set forth in this publication is provided exclusively with the view to facilitating the selection of a product and/or service. The information contained in this publication is based on actual laboratory data and/or field test experience. We believe this information to be accurate, but do not guarantee in any manner its suitability to the user's process or assume any liability arising out of its use or performance. The user, by ordering the products and/or services described herein, agrees to be entirely responsible for thoroughly testing any application to determine its suitability before committing to production. It is key for the user to determine the properties of its own products and/or compounds when using a product and/or service herein described. We do not give any representation or warranty, express or implied, as to the accuracy or completeness of the data and information contained in this document, and shall have no liability to the user or any other person resulting from the use of or reliance on any such information. Further, we do not give any representation or warranty, express or implied, as to our products and/or services, including in respect of their merchantability and fitness for a particular purpose, and shall have no liability to the user or any other person resulting from the use of or reliance on any such products and/or services. Only those representations and warranties set forth in a supply agreement, when, as and if it is executed, and subject to such limitations and restrictions as may be set forth in such agreement, shall have any legal effect. Statements included in this document are not, and may not be construed as, representations or warranties or as inducements to infringe any patent or violate any law, safety code or insurance regulation. 3B reserves the right to modify the content of present document without notice and without incurring in any obligations.